

7
Claims

What is claimed is:

1. A method of manufacturing a luminescent screen for cathode-ray tubes having deposits of phosphor powder on an interior of a faceplate comprises:

5 applying a film formulation over said deposits to form a lacquer film, said film formulation having at least one lacquer material and at least two solvents, one of said solvents being a non-solvent for at least one lacquer material;

 applying a thin layer of aluminum on said film; and

 exposing said screen to a sufficiently high temperature to volatilize any organic
10 components.

2. The method of claim 1, wherein said lacquer material contains at least one acrylic resin.

3. The method of claim 1, wherein said film formulation comprises
15 polymethylmethacrylate (PMMA); methyl isobutyl ketone (MIBK), a solvent for PMMA; and linalyl acetate (LA), a solvent in which PMMA is not soluble.

4. The method of claim 1, wherein said film formulation is applied by electrostatic
20 spraying.

5. The method of claim 1, wherein said film formulation is applied by spin coating.

6. The method of claim 1, wherein at least one type of microcrystals, which is
25 selected from the group of boric acid, ammonium oxalate, or oxalic acid, is applied to said film prior to applying said film formulation.

7. A method of manufacturing a luminescent screen for cathode-ray tubes having fixed phosphor elements that comprises:

30 electrostatically spraying a film formulation on to said fixed phosphor elements resulting in a lacquer film, wherein said formulation has at least one lacquer material and at least two solvents, one of said solvents being a non-solvent for at least one lacquer material;

10027889-102504

applying a thin layer of aluminum on said film; and
exposing said screen to a sufficiently high temperature to volatilize any organic
components.

5 8. The method of claim 7, wherein said film formulation comprises concentrations
of 81.0 % wt. MIBK, 4.0 % wt. LA, and 15.0 % wt. PMMA.

9. The method of claim 7, wherein said lacquer film contains at least one acrylic
resin.

10 10. The method of claim 7, wherein said fixed phosphor elements are stripes.

11. The method of claim 7, wherein said fixed phosphor elements are dots.

15 12. A method of manufacturing a luminescent screen, for a cathode-ray tube
having electrophotographically printed phosphor elements, that comprises:
fixing said phosphor elements by applying a suitable fixative with electrostatic
spray of a solvent or solvents onto the panel, whereby said OPC is dissolved and
encapsulates individual phosphor particles resulting in fixed phosphor elements;
20 applying a film formulation over said fixed phosphor elements to form a
lacquer film, wherein said film formulation contains methyl isobutyl ketone (MIBK),
linalyl acetate (LA), and polymethylmethacrylate (PMMA);
applying a thin layer of aluminum on said film; and
exposing said screen to about 450 °C to volatilize all of the organic
25 components.

13. The method of claim 12, wherein said film formulation comprises concentration
ranges of 79 to 93 % wt. of MIBK, 2 to 6 % wt. of LA, and 5 to 15 % wt. of PMMA.

30 14. The method of claim 12, wherein said fixed phosphor elements are in the form
of stripes.

15. The method of claim 12, wherein said fixed phosphor elements are in the form of dots.

16. The method of claim 12, further comprises measuring gloss of said thin layer aluminum before exposing the screen to about 450 °C and evaluating values of gloss such that values exceeding a threshold figure will be further processed and those not meeting said figure are scrapped.

17. The method of claim 12, further comprises measuring gloss of said thin layer of aluminum after exposing the screen to 450 °C and evaluating values of gloss such that values exceeding a threshold figure will be further processed and those not meeting said figure are scrapped.

10
10027889.10237
15